



# GENERAL FINISHES

PO Box 510567 New Berlin, WI 53151  
800-783-6050 Fax 262-786-6509

*Oil Based*

## Danish Oil

### Classification:

Oil Based Stain

### Product Description:

General Finishes Danish Oil's traditional blend of linseed oil and gilsonite colorant penetrates and colors wood unlike pigmented stains. Gilsonite possesses a unique black walnut color different from pigments. Danish Oil's best use is on oak where the walnut colors a carried deep into the grain and produce a look that pigments cannot match. The linseed oil in Danish Oil dries to a durable finish. Multiple coats help build durability, however for maximum protection, topcoat with General Finishes Arm-R-Seal, Pre-Cat Lacquer, or Conversion Varnish. It is available in a variety of colors.

### Application:

Apply via applicator, wiping cloth, brush or spray. Stir well before application. Apply liberal amount of stain to the surface and allow to penetrate several minutes before wiping with a clean paper towel or cloth. A second coat may be applied to darken the color. Compressed air: 0.40" fluid tip / medium cap; HVLP: 0.051" fluid tip / medium cap. Allow 24 -48 hours dry before topcoating.

### Product Data:

- Density: 6.9 – 7.2 lbs. / gal
- Weight Solids: 38 - 50% (color dependant)
- Volume Solids: 33 - 46%
- Viscosity: 18 - 30 seconds
- Method: #4 Ford
- pH: NA
- V.O.C.: <550 g/l ( 4.59 lbs/gal)
  
- % VOC: 50 - 62%
- Coverage: Approx. 800 sq. ft. / gal

### Container:

Pints, Quarts, Gallons, Fives and Drums

### Sheen:

Not Applicable

### Dry Time 70°F and 70% R.H:

- Dry: 6 - 24 hours
- To Topcoat: 24 -48 hours

## GENERAL FINISHES

*"The Country's Finest Full Line Manufacturer of Wood Finishing Products"*

[www.generalfinishes.com](http://www.generalfinishes.com)



**GENERAL FINISHES**  
PO Box 510567 New Berlin, WI 53151 800-783-6050

### Mixing and Application:

- Catalyst Ratio: None
- Pot Life: Not Applicable
- Shelf Life: 1 year, minimum
- Reducer/Thinner: Mineral Spirits (10 -20%)

### Sealer & Finish Recommendation:

Can be topcoated with most oil base and solvent base finishes, varnishes, & lacquers. Test adhesion and compatibility on all other systems.

General Finishes Vinyl Sealer recommended if not using a self sealing finish or optimum build and smoothness is desired. Use: Oil Base: General Finishes Arm-R-Seal. Solvent Base: General Finishes Pre-Cat Lacquer or Conversion Varnish.

### Surface Preparation:

Surface must be clean, dry and free of dust, dirt, grease, wax, or contaminants. For soft woods, sand with #120 grit & finish with #150 -#180. For hard woods, sand with #100 grit & finish with #120. Fill all nail holes or cracks using a stain-accepting filler or putty. Remove all dust by vacuuming or wiping with a damp cloth. Do not use tack cloths which contain linseed oils.

### Application:

- Conventional Spray
- Air Assisted Airless
- HVLP
- Brush
- Pad Applicator
- Clean wiping cloth

### Cautions:

- Mix container before use
- Use with proper ventilation
- Read MSDS for safety information

### Clean-up Information:

For best results, clean all equipment with Mineral Spirits.

**Danish Oil**  
071305

---

NOTICE: All of the above statements, recommendations, suggestions, and data concerning the subject material are based on laboratory results and believed to be reliable. We expressly do not represent, warrant, or guarantee the accuracy, completeness or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like and (THE MANUFACTURER DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED,) OF MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE.

---